

BITUMEN R25/85

Test method

Specification

d-70

1.05 approx

Penetration @25 C

d-5

10/20

Softening point C

d-36

80/90

Ductility @25 C

D-113

3 min

Loss on heating (wt)%

d-6

0.2 max

Flash point C

d-92

225max

Solubility in CS₂ (wt)%

d-4

99 min

Specific gravity @25/25 C