

Bitumen 60/70

	Test method	Specification
D-70	1.01-1.06	Specific gravity @25/25 C
D-5	60/70	Penetration @25 C
D-36	49/56	Softening point C
D-113	100 min	Ductility @25 C
D-6	0.2 max	Loss on heating (wt)%
D-6 & D-5	20 max	Drop in penetration after heating %
D-92	250min	Flash point C
D-4	99.5 min	Solubility in CS2 (wt)%
*A.A.S.H.O.T.102	negative	Spot test